

This Page Is Inserted by IFW Operations  
and is not a part of the Official Record

## **BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning documents *will not* correct images,  
please do not report the images to the  
Image Problem Mailbox.**

## PCT COOPERATION TREA

PCT

NOTIFICATION OF THE RECORDING  
OF A CHANGE(PCT Rule 92bis.1 and  
Administrative Instructions, Section 422)

From the INTERNATIONAL BUREAU

To:

HERMAN DE GROOT, Johan, Willem  
Corus Technology BV  
P.O. Box 10000  
NL-1970 CA Ijmuiden  
PAYS-BAS

Date of mailing (day/month/year) 06 July 2000 (06.07.00)	<b>IMPORTANT NOTIFICATION</b>  International filing date (day/month/year) 29 October 1999 (29.10.99)
Applicant's or agent's file reference AL182PCT/Do/H	
International application No. PCT/EP99/08316	

## 1. The following indications appeared on record concerning:

☐ the applicant      ☐ the inventor      ☒ the agent      ☐ the common representative

## Name and Address

 HANSEN, Willem, Joseph, Maria  
 Corus Technology BV  
 P.O. Box 10000  
 NL-1970 CA Ijmuiden  
 Netherlands

State of Nationality

State of Residence

Telephone No.

Facsimile No.

Teleprinter No.

## 2. The International Bureau hereby notifies the applicant that the following change has been recorded concerning:

☐ the person      ☒ the name      ☐ the address      ☐ the nationality      ☐ the residence

## Name and Address

 HANSEN, Willem, Joseph, Maria  
 Corus Technology BV  
 P.O. Box 10000  
 NL-1970 CA Ijmuiden  
 Netherlands

State of Nationality

State of Residence

Telephone No.

0251/496956

Facsimile No.

0251/470252

Teleprinter No.

## 3. Further observations, if necessary:

**Please also note the change in the agent's address as specified in the addressee box above.**

## 4. A copy of this notification has been sent to:

☒ the receiving Office      ☐ the designated Offices concerned  
☐ the International Searching Authority      ☒ the elected Offices concerned  
☒ the International Preliminary Examining Authority      ☐ other:

 The International Bureau of WIPO  
 34, chemin des Colombettes  
 1211 Geneva 20, Switzerland

Facsimile No.: (41-22) 740.14.35

Authorized officer

Beate Giffo-Schmitt

Telephone No.: (41-22) 338.83.38

## PATENT COOPERATION T. ATY

PCT

NOTIFICATION OF THE RECORDING  
OF A CHANGE(PCT Rule 92bis.1 and  
Administrative Instructions, Section 422)

From the INTERNATIONAL BUREAU

To:

HERMAN DE GROOT, Johan, Willem  
Corus Technology BV  
P.O. Box 10000  
NL-1970 CA Ijmuiden  
PAYS-BAS

Date of mailing (day/month/year) 04 July 2000 (04.07.00)	IMPORTANT NOTIFICATION
Applicant's or agent's file reference AL182PCT/Do/H	
International application No. PCT/EP99/08316	International filing date (day/month/year) 29 October 1999 (29.10.99)

## 1. The following indications appeared on record concerning:

☒ the applicant
 ☐ the inventor
 ☐ the agent
 ☐ the common representative

## Name and Address

 HOOGOVENS ALUMINIUM WALZPRODUKTE  
GMBH  
Carl-Spaeter-Strasse 10  
D-56070 Koblenz  
Germany

## State of Nationality

DE

## State of Residence

DE

## Telephone No.

## Facsimile No.

## Teleprinter No.

## 2. The International Bureau hereby notifies the applicant that the following change has been recorded concerning:

☐ the person
 ☒ the name
 ☐ the address
 ☐ the nationality
 ☐ the residence

## Name and Address

 CORUS ALUMINIUM WALZPRODUKTE GMBH  
Carl-Spaeter-Strasse 10  
D-56070 Koblenz  
Germany

## State of Nationality

DE

## State of Residence

DE

## Telephone No.

## Facsimile No.

## Teleprinter No.

## 3. Further observations, if necessary:

## 4. A copy of this notification has been sent to:

<input checked="" type="checkbox"/> the receiving Office	<input type="checkbox"/> the designated Offices concerned
<input type="checkbox"/> the International Searching Authority	<input checked="" type="checkbox"/> the elected Offices concerned
<input checked="" type="checkbox"/> the International Preliminary Examining Authority	<input type="checkbox"/> other:

 The International Bureau of WIPO  
34, chemin des Colombettes  
1211 Geneva 20, Switzerland

Facsimile No.: (41-22) 740.14.35

## Authorized officer

A. Karkachi

Telephone No.: (41-22) 338.83.38

PCT

NOTIFICATION OF THE RECORDING  
OF A CHANGE

(PCT Rule 92bis.1 and  
Administrative Instructions, Section 422)

From the INTERNATIONAL BUREAU

To:

HERMAN DE GROOT, Johan, Willem  
Corus Technology BV  
P.O. Box 10000  
NL-1970 CA IJmuiden  
PAYS-BAS

Date of mailing (day/month/year) 07 June 2000 (07.06.00)	
Applicant's or agent's file reference AL182PCT/Do/H	IMPORTANT NOTIFICATION
International application No. PCT/EP99/08316	International filing date (day/month/year) 29 October 1999 (29.10.99)

1. The following indications appeared on record concerning:

☐ the applicant ☐ the inventor ☒ the agent ☐ the common representative

Name and Address HERMAN DE GROOT, Johan, Willem Hoogovens Corporate Services BV P.O. Box 10000 NL-1970 CA IJmuiden Netherlands	State of Nationality	State of Residence
	Telephone No. +31/251-491-812	
	Facsimile No. +31/251-470-252	
	Teleprinter No. 35211 hovs nl	

2. The International Bureau hereby notifies the applicant that the following change has been recorded concerning:

☐ the person ☐ the name ☒ the address ☐ the nationality ☐ the residence

Name and Address HERMAN DE GROOT, Johan, Willem Corus Technology BV P.O. Box 10000 NL-1970 CA IJmuiden Netherlands	State of Nationality	State of Residence
	Telephone No. +31/251-491-812	
	Facsimile No. +31/251-470-252	
	Teleprinter No. 35211 hovs nl	

3. Further observations, if necessary:

4. A copy of this notification has been sent to:

☒ the receiving Office ☐ the designated Offices concerned  
☐ the International Searching Authority ☒ the elected Offices concerned  
☒ the International Preliminary Examining Authority ☐ other:

The International Bureau of WIPO 34, chemin des Colombettes 1211 Geneva 20, Switzerland Facsimile No.: (41-22) 740.14.35	Authorized officer C. Cupello Telephone No.: (41-22) 338.83.38
---	--

# PCT COOPERATION TREATY

**PCT**

## NOTIFICATION OF THE RECORDING OF A CHANGE

(PCT Rule 92bis.1 and  
Administrative Instructions, Section 422)

From the INTERNATIONAL BUREAU

To:


HERMAN DE GROOT, Johan, Willem  
Corus Technology BV  
P.O. Box 10000  
NL-1970 CA IJmuiden  
PAYS-BAS

<b>Date of mailing (day/month/year)</b> 07 June 2000 (07.06.00)	
<b>Applicant's or agent's file reference</b> AL182PCT/Do/H	<b>IMPORTANT NOTIFICATION</b>
<b>International application No.</b> PCT/EP99/08316	<b>International filing date (day/month/year)</b> 29 October 1999 (29.10.99)

1. The following indications appeared on record concerning: <input checked="" type="checkbox"/> the applicant <input checked="" type="checkbox"/> the inventor <input type="checkbox"/> the agent <input type="checkbox"/> the common representative		
<b>Name and Address</b> HASZLER, Alfred, Johann, Peter Auf'm Gräverich 31 D-56179 Vallendar Germany	<b>State of Nationality</b> DE	<b>State of Residence</b> DE
Telephone No.		
Facsimile No.		
Teleprinter No.		
2. The International Bureau hereby notifies the applicant that the following change has been recorded concerning: <input type="checkbox"/> the person <input type="checkbox"/> the name <input type="checkbox"/> the address <input checked="" type="checkbox"/> the nationality <input type="checkbox"/> the residence		
<b>Name and Address</b> HASZLER, Alfred, Johann, Peter Auf'm Gräverich 31 D-56179 Vallendar Germany	<b>State of Nationality</b> AT	<b>State of Residence</b> DE
Telephone No.		
Facsimile No.		
Teleprinter No.		
3. Further observations, if necessary:		
4. A copy of this notification has been sent to: <div style="display: flex; justify-content: space-between;"> <div> <input checked="" type="checkbox"/> the receiving Office  <input type="checkbox"/> the International Searching Authority  <input checked="" type="checkbox"/> the International Preliminary Examining Authority                         </div> <div> <input type="checkbox"/> the designated Offices concerned  <input checked="" type="checkbox"/> the elected Offices concerned  <input type="checkbox"/> other:                         </div> </div>		

<b>The International Bureau of WIPO</b> 34, chemin des Colombettes 1211 Geneva 20, Switzerland  Facsimile No.: (41-22) 740.14.35	<b>Authorized officer</b>  C. Cupello  Telephone No.: (41-22) 338.83.38
--	---

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification <sup>7</sup> : <b>B32B 3/28, 15/01, C22C 21/06</b></p>	<b>A1</b>	<p>(11) International Publication Number: <b>WO 00/26020</b></p> <p>(43) International Publication Date: <b>11 May 2000 (11.05.00)</b></p>						
<p>(21) International Application Number: <b>PCT/EP99/08316</b></p> <p>(22) International Filing Date: <b>29 October 1999 (29.10.99)</b></p> <p>(30) Priority Data:</p> <table style="width: 100%; border: none;"> <tr> <td style="width: 30%;">98203665.9</td> <td style="width: 30%;">30 October 1998 (30.10.98)</td> <td style="width: 40%;">EP</td> </tr> <tr> <td>99201767.3</td> <td>4 June 1999 (04.06.99)</td> <td>EP</td> </tr> </table> <p>(71) Applicant (for all designated States except US): <b>HOOGOVENS ALUMINIUM WALZPRODUKTE GMBH [DE/DE]; Carl-Spaeter-Strasse 10, D-56070 Koblenz (DE).</b></p> <p>(72) Inventors; and</p> <p>(75) Inventors/Applicants (for US only): <b>HASZLER, Alfred, Johann, Peter [DE/DE]; Auf'm Gräverich 31, D-56179 Vallendar (DE). SAMPATH, Desikan [IN/NL]; Waalstraat 122, NL-1946 RH Beverwijk (NL). MECHSNER, Klaus, Alfons [DE/DE]; Heimstrasse 70, D-56566 Niewied (DE).</b></p> <p>(74) Agent: <b>HERMAN DE GROOT, Johan, Willem; Hoogovens Corporate Services BV, P.O. Box 10000, NL-1970 CA IJmuiden (NL).</b></p>			98203665.9	30 October 1998 (30.10.98)	EP	99201767.3	4 June 1999 (04.06.99)	EP
98203665.9	30 October 1998 (30.10.98)	EP						
99201767.3	4 June 1999 (04.06.99)	EP						
<p>(81) Designated States: <b>AE, AL, AM, AT, AT (Utility model), AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, CZ (Utility model), DE, DE (Utility model), DK, DK (Utility model), DM, EE, EE (Utility model), ES, FI, FI (Utility model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</b></p> <p><b>Published</b></p> <p><i>With international search report.</i></p> <p><i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>								
<p>(54) Title: <b>COMPOSITE ALUMINIUM PANEL</b></p> <div style="text-align: center; margin: 20px 0;">  </div>								
<p>(57) Abstract</p> <p>A composite aluminium panel comprising two parallel plates and/or sheets secured to the peaks and troughs of a corrugated aluminium stiffener sheet between the parallel plates and/or sheets, wherein the corrugated aluminium stiffener sheet is made from an aluminium alloy rolled sheet of composition (in weight percent): Mg 1.5–6.0, Mn 0.3–1.4, Zn 0.4–5.0, Fe up to 0.5, Si up to 0.5, Zr up to 0.30, optionally, one or more of (Cr 0.05–0.30, Ti 0.01–0.20, V 0.05–0.25, Ag 0.05–0.40, Cu up to 0.40), others up to 0.05 each, 0.15 total, Al balance, and having in an H-condition or in the O-condition a ratio of PS/UTS in the range of 0.4 to 0.9 and having good roll formability.</p>								

# PATENT COOPERATION TREATY

202-01  
20.02-2

From the  
INTERNATIONAL PRELIMINARY EXAMINING AUTHORITY

20 FEB 2001  
PCT

To:

HANSEN, Willem J.M.  
CORUS TECHNOLOGY BV  
P.O. Box 10000  
NL-1970 CA IJmuiden  
PAYS-BAS

NOTIFICATION OF TRANSMITTAL OF  
THE INTERNATIONAL PRELIMINARY  
EXAMINATION REPORT  
(PCT Rule 71.1)

Date of mailing  
(day/month/year) 16.02.2001

Applicant's or agent's file reference  
AL182PCT/Do/H

## IMPORTANT NOTIFICATION

International application No.  
PCT/EP99/08316

International filing date (day/month/year)  
29/10/1999

Priority date (day/month/year)  
30/10/1998

Applicant  
CORUS ALUMINIUM WALZPRODUKTE GMBH et al.

1. The applicant is hereby notified that this International Preliminary Examining Authority transmits herewith the international preliminary examination report and its annexes, if any, established on the international application.
2. A copy of the report and its annexes, if any, is being transmitted to the International Bureau for communication to all the elected Offices.
3. Where required by any of the elected Offices, the International Bureau will prepare an English translation of the report (but not of any annexes) and will transmit such translation to those Offices.

### 4. REMINDER

The applicant must enter the national phase before each elected Office by performing certain acts (filing translations and paying national fees) within 30 months from the priority date (or later in some Offices) (Article 39(1)) (see also the reminder sent by the International Bureau with Form PCT/IB/301).

Where a translation of the international application must be furnished to an elected Office, that translation must contain a translation of any annexes to the international preliminary examination report. It is the applicant's responsibility to prepare and furnish such translation directly to each elected Office concerned.

For further details on the applicable time limits and requirements of the elected Offices, see Volume II of the PCT Applicant's Guide.

Name and mailing address of the IPEA/

European Patent Office - P.B. 5818 Patentlaan 2  
NL-2280 HV Rijswijk - Pays Bas  
Tel. +31 70 340 - 2040 Tx: 31 651 epo nl  
Fax: +31 70 340 - 3016

Authorized officer

Sinanovic, E

Tel.+31 70 340-2672



# PATENT COOPERATION TREATY

# PCT

## INTERNATIONAL SEARCH REPORT

(PCT Article 18 and Rules 43 and 44)

Applicant's or agent's file reference <b>AL182PCT/Do/H</b>	<b>FOR FURTHER ACTION</b>		see Notification of Transmittal of International Search Report (Form PCT/ISA/220) as well as, where applicable, item 5 below.
International application No. <b>PCT/EP 99/ 08316</b>	International filing date (day/month/year) <b>29/10/1999</b>	(Earliest) Priority Date (day/month/year) <b>30/10/1998</b>	

Applicant

**HOOGO VENS ALUMINIUM WALZPRODUKTE GMBH et al.**

This International Search Report has been prepared by this International Searching Authority and is transmitted to the applicant according to Article 18. A copy is being transmitted to the International Bureau.

This International Search Report consists of a total of 3 sheets.



It is also accompanied by a copy of each prior art document cited in this report.

**1. Basis of the report**

- a. With regard to the language, the international search was carried out on the basis of the international application in the language in which it was filed, unless otherwise indicated under this item.



the international search was carried out on the basis of a translation of the international application furnished to this Authority (Rule 23.1(b)).

- b. With regard to any nucleotide and/or amino acid sequence disclosed in the international application, the international search was carried out on the basis of the sequence listing:



contained in the international application in written form.



filed together with the international application in computer readable form.



furnished subsequently to this Authority in written form.



furnished subsequently to this Authority in computer readable form.



the statement that the subsequently furnished written sequence listing does not go beyond the disclosure in the international application as filed has been furnished.



the statement that the information recorded in computer readable form is identical to the written sequence listing has been furnished

2. ☐ Certain claims were found unsearchable (See Box I).

3. ☐ Unity of invention is lacking (see Box II).

**4. With regard to the title,**



the text is approved as submitted by the applicant.



the text has been established by this Authority to read as follows:

**5. With regard to the abstract,**



the text is approved as submitted by the applicant.



the text has been established, according to Rule 38.2(b), by this Authority as it appears in Box III. The applicant may, within one month from the date of mailing of this international search report, submit comments to this Authority.

**6. The figure of the drawings to be published with the abstract is Figure No.**



as suggested by the applicant.



because the applicant failed to suggest a figure.



because this figure better characterizes the invention.

4



None of the figures.



# INTERNATIONAL SEARCH REPORT

Internal Application No

**PCT/EP 99/08316**

#### A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 B32B3/28 B32B15/01 C22C21/06

According to International Patent Classification (IPC) or to both national classification and IPC

### B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C22C B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

### C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	GB 2 182 703 A (HUNTER GEORGE WILLIAM) 20 May 1987 (1987-05-20) page 2, line 13 - line 66; figure 1	1
A	EP 0 799 900 A (HOOGO VENS ALU WALZPROD GMBH) 8 October 1997 (1997-10-08) claim 1	1
A	EP 0 823 489 A (PECHINEY RHENALU) 11 February 1998 (1998-02-11) claim 1	1
A	EP 0 557 597 A (REX PATENT) 1 September 1993 (1993-09-01) claim 1; figure 1	1

-/-

**X** Further documents are listed in the continuation of box C.

**Y** Patent family members are listed in annex.

° Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T"** later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X"** document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y"** document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
- "Z"** document member of the same patent family

Date of the actual completion of the international search

**29 February 2000**

Date of mailing of the international search report

08/03/2000

Name and mailing address of the ISA  
European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,  
Fax (+31-70) 340-3016

Authorized officer

**Gregg, N**

# INTERNATIONAL SEARCH REPORT

International Application No.

PCT/EP 99/08316

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	AMERICAN SOCIETY FOR METALS: "Metals Handbook, 9th Ed, Vol 14", FORMING AND FORGING, US, METALS PARK, ASM, VOL. VOL. 14, PAGE(S) 624-635-635 XP002097173	
A	US 5 821 506 A (MATSEN MARC R) 13 October 1998 (1998-10-13)	
A	J E HATCH: "Aluminium - Properties and Physical Metallurgy", US, OHIO, AMERICAN SOCIETY FOR METALS, PAGE(S) 372-374 XP002097155	
A	US 5 534 354 A (KISTNER MATTHEW G ET AL) 9 July 1996 (1996-07-09)	

# INTERNATIONAL SEARCH REPORT

information on patent family members

Inter. Application No

PCT/EP 99/08316

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
GB 2182703	A	20-05-1987	CA 1316642 A	27-04-1993
EP 0799900	A	08-10-1997	AU 2293397 A	29-10-1997
			CA 2250977 A	16-10-1997
			CN 1217030 A	19-05-1999
			WO 9738146 A	16-10-1997
			EP 0892858 A	27-01-1999
			JP 11507102 T	22-06-1999
			NO 984634 A	02-10-1998
EP 0823489	A	11-02-1998	FR 2752244 A	13-02-1998
			AU 709909 B	09-09-1999
			AU 3320197 A	12-02-1998
			DE 823489 T	16-07-1998
			JP 10088270 A	07-04-1998
			US 5908518 A	01-06-1999
EP 0557597	A	01-09-1993	DE 4141855 A	24-06-1993
			DE 59209763 D	09-12-1999
US 5821506	A	13-10-1998	US 5700995 A	23-12-1997
			US 5420400 A	30-05-1995
			US 5410132 A	25-04-1995
			US 5705794 A	06-01-1998
			US 5914064 A	22-06-1999
			US 5530227 A	25-06-1996
			US 5599472 A	04-02-1997
			US 5793024 A	11-08-1998
			US 5808281 A	15-09-1998
			US 5624594 A	29-04-1997
			US 5728309 A	17-03-1998
			US 5645744 A	08-07-1997
			US 5710414 A	20-01-1998
			US 5723849 A	03-03-1998
			US 5641422 A	24-06-1997
			US 5587098 A	24-12-1996
			US 5847375 A	08-12-1998
			US 5683607 A	04-11-1995
			US 5571436 A	05-11-1996
			US 5591370 A	07-01-1997
			US 5683608 A	04-11-1997
			US 5747179 A	05-05-1998
			US 5591369 A	07-01-1997
US 5534354	A	09-07-1996	US 5451472 A	19-09-1995
			US 5330092 A	19-07-1995

PATENT COOPERATION TREATY

PCT

REC'D 20 FEB 2001

WIPO

PCT

# INTERNATIONAL PRELIMINARY EXAMINATION REPORT

(PCT Article 36 and Rule 70)


Applicant's or agent's file reference <b>AL182PCT/Do/H</b>	<b>FOR FURTHER ACTION</b> See Notification of Transmittal of International Preliminary Examination Report (Form PCT/IPEA/416)	
International application No. <b>PCT/EP99/08316</b>	International filing date (day/month/year) <b>29/10/1999</b>	Priority date (day/month/year) <b>30/10/1998</b>
International Patent Classification (IPC) or national classification and IPC <b>B32B3/28</b>		
Applicant <b>CORUS ALUMINIUM WALZPRODUKTE GMBH et al.</b>		

1. This international preliminary examination report has been prepared by this International Preliminary Examining Authority and is transmitted to the applicant according to Article 36.
2. This REPORT consists of a total of 4 sheets, including this cover sheet.
  - ☐ This report is also accompanied by ANNEXES, i.e. sheets of the description, claims and/or drawings which have been amended and are the basis for this report and/or sheets containing rectifications made before this Authority (see Rule 70.16 and Section 607 of the Administrative Instructions under the PCT).

These annexes consist of a total of sheets.

3. This report contains indications relating to the following items:

- I ☒ Basis of the report
- II ☐ Priority
- III ☐ Non-establishment of opinion with regard to novelty, inventive step and industrial applicability
- IV ☐ Lack of unity of invention
- V ☒ Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement
- VI ☐ Certain documents cited
- VII ☐ Certain defects in the international application
- VIII ☐ Certain observations on the international application

Date of submission of the demand  <b>21/04/2000</b>	Date of completion of this report  <b>16.02.2001</b>
Name and mailing address of the international preliminary examining authority:   <b>European Patent Office - P.B. 5818 Patentlaan 2 NL-2280 HV Rijswijk - Pays Bas Tel. +31 70 340 - 2040 Tx: 31 651 epo nl Fax: +31 70 340 - 3016</b>	Authorized officer  <b>Gregg, N</b>  Telephone No. <b>+31 70 340 3574</b> <div data-bbox="1396 1848 1542 1995" data-label="Image"> </div>

# INTERNATIONAL PRELIMINARY EXAMINATION REPORT

International application No. PCT/EP99/08316

## I. Basis of the report

1. This report has been drawn on the basis of (*substitute sheets which have been furnished to the receiving Office in response to an invitation under Article 14 are referred to in this report as "originally filed" and are not annexed to the report since they do not contain amendments.*):

### Description, pages:

1-15 as originally filed

### Claims, No.:

1-14 as originally filed

### Drawings, sheets:

1/4-4/4 as originally filed

2. The amendments have resulted in the cancellation of:

- ☐ the description, pages:
- ☐ the claims, Nos.:
- ☐ the drawings, sheets:

3. ☐ This report has been established as if (some of) the amendments had not been made, since they have been considered to go beyond the disclosure as filed (Rule 70.2(c)):

4. Additional observations, if necessary:

**INTERNATIONAL PRELIMINARY  
EXAMINATION REPORT**

International application No. PCT/EP99/08316

**V. Reasoned statement under Article 35(2) with regard to novelty, inventive step or industrial applicability; citations and explanations supporting such statement**

**1. Statement**

Novelty (N)	Yes:	Claims	1-14
	No:	Claims	
Inventive step (IS)	Yes:	Claims	1-14
	No:	Claims	
Industrial applicability (IA)	Yes:	Claims	1-14
	No:	Claims	

**2. Citations and explanations**

**see separate sheet**

**V.Statement under Rule 35(2)**

The application relates to a composite aluminium panel having two outer, parallel surfaces which is strengthened with a corrugated aluminium stiffener sheet of the composition type Al-Mg-Mn-Zn as defined in claim 1 and use claims 10 and 11.

None of the prior art discloses a corrugated stiffener of this composition and the subject-matter of claims 1-14 is novel (Art.33(2) PCT).

The problem to be solved is to provide a corrugated stiffener having good strength, good weldability and good formability such as for roll forming. The closest prior art is represented by EP-A-799900 and EP-A-823489 which disclose alloy compositions falling within the range of the presently defined stiffener composition which are weldable and corrosion resistant. However, there is no derivable information regarding their formability such as to make them suitable for roll forming nor any indication as to their suitability for use in composite panels. Further, the prior art compositions are disclosed in combination with large welded marine structures in the form of thick plate and not thinner sheet for corrugated panels. The subject-matter of claims 1-14 is therefore inventive (Art. 33(3) PCT).

The application is industrially applicable in the production of composite panels used, for example, in ship building.



## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 7 :  
B32B 3/28, 15/01, C22C 21/06

A1

(11) International Publication Number: WO 00/26020

(43) International Publication Date: 11 May 2000 (11.05.00)

(21) International Application Number: PCT/EP99/08316

(22) International Filing Date: 29 October 1999 (29.10.99)

(30) Priority Data:

98203665.9 30 October 1998 (30.10.98) EP  
99201767.3 4 June 1999 (04.06.99) EP

(71) Applicant (for all designated States except US): HOOGOVS  
ALUMINIUM WALZPRODUKTE GMBH [DE/DE];  
Carl-Spaeter-Strasse 10, D-56070 Koblenz (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): HASZLER, Alfred, Jo-  
hann, Peter [DE/DE]; Auf'm Gräverich 31, D-56179 Val-  
lendar (DE). SAMPATH, Desikan [IN/NL]; Waalstraat 122,  
NL-1946 RH Beverwijk (NL). MECHSNER, Klaus, Alfons  
[DE/DE]; Heimstrasse 70, D-56566 Niewied (DE).

(74) Agent: HERMAN DE GROOT, Johan, Willem; Hoogovens  
Corporate Services BV, P.O. Box 10000, NL-1970 CA  
Ijmuiden (NL).


(81) Designated States: AE, AL, AM, AT, AT (Utility model), AU,  
AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, CZ  
(Utility model), DE, DE (Utility model), DK, DK (Utility  
model), DM, EE, EE (Utility model), ES, FI, FI (Utility  
model), GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS,  
JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV,  
MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO,  
RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, TZ, UA,  
UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM,  
KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent  
(AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent  
(AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT,  
LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI,  
CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

Published

With international search report.

Before the expiration of the time limit for amending the  
claims and to be republished in the event of the receipt of  
amendments.

(54) Title: COMPOSITE ALUMINIUM PANEL



(57) Abstract

A composite aluminium panel comprising two parallel plates and/or sheets secured to the peaks and troughs of a corrugated aluminium stiffener sheet between the parallel plates and/or sheets, wherein the corrugated aluminium stiffener sheet is made from an aluminium alloy rolled sheet of composition (in weight percent): Mg 1.5–6.0, Mn 0.3–1.4, Zn 0.4–5.0, Fe up to 0.5, Si up to 0.5, Zr up to 0.30, optionally, one or more of (Cr 0.05–0.30, Ti 0.01–0.20, V 0.05–0.25, Ag 0.05–0.40, Cu up to 0.40), others up to 0.05 each, 0.15 total, Al balance, and having in an H-condition or in the O-condition a ratio of PS/UTS in the range of 0.4 to 0.9 and having good roll formability.



**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

## COMPOSITE ALUMINIUM PANEL

### FIELD OF THE INVENTION

This invention is concerned with a composite aluminium panel comprising two  
5 parallel plates and/or sheets secured to a stiffener sheet between the parallel plates  
and/or sheets, and with the use the composite aluminium panel in structural materials  
such as in the construction of large welded structures.

For the purpose of this invention sheet material is to be understood as a rolled  
product having a thickness of not more than 6.0 mm.

10

### DESCRIPTION OF THE RELATED ART

Currently large welded structures such as the floor or cargo decks of a ship like a  
catamaran are built by welding together a large number of extruded sections of standard  
AA6000-series alloys such as the AA6082 alloy. A typical construction involves fusion  
15 welding of a large number of hollow and/or simple sections. Typically hollow sections  
of the AA6082 alloy are used since this alloy allows the designers to achieve significant  
weight reductions. This is mainly due to the fact that AA6082 alloy is the strongest of  
commercially available standard AA6000-series alloys. Because of the limitations  
imposed by extrudability of the AA6082 alloy, the minimum wall thickness for hollow  
20 sections is practically restricted to the range 2.5-4.0 mm depending on the design of the  
extruded section. This practical limitation on minimum wall thickness in turn limits the  
weight savings that can be achieved by improving the design.

Alternatively large engineering structures such as cargo or passenger decks of a  
ship can be constructed by joining pre-fabricated aluminium products produced by  
25 joining and/or welding of a number of roll formed corrugated sheets. The realisation of  
this approach relies on the availability of high strength corrugated aluminium alloy  
product shapes. This requires aluminium alloy sheets that are not only easy to roll form  
but also have higher strength. Standard available aluminium alloy feed stock for roll  
forming such as AA3004 alloy do not develop high enough strength to achieve  
30 significant weight reduction.

Within the scope of this invention roll forming, also known as contour roll  
forming or cold roll forming, is understood to be a continuous process for forming

metal from sheet, strip, or coiled stock into desired shapes of essentially uniform thickness by feeding the stock through a series of roll stations equipped with contoured rolls, see Metals Handbook, 9th. edition, Vol.14, ASM International, 1988, pp.624-635.

Some disclosure of structures found in the prior art literature will be mentioned  
5 below.

US 5,821,506 discloses a complex aerodynamically smooth exterior surface part made from an inductive superplastically formed part free of diffusion bonds, having at least four sheets, and having a primary dimension, comprising (a) an inner core having two faces defined by at lest two inductive superplastically formed core sheets made  
10 from superplastically alloys of titanium or aluminium, and (b) outer face sheets of superplastic alloys of titanium or aluminium brazed to the two faces of the core by a bronze alloy ribbon one face sheet on each face of the core.

US 5,534,354 discloses a method of providing a superplastic form sandwich structure airfoil.

15 EP-A-0432308 discloses a multi-layer metal structures having heat insulation characteristics and is being made of alloys exhibiting superplasticity and which are capable of being subjected to superplastic forming. The structures are especially adapted for use in supersonic and hypersonic aircraft.

## 20 SUMMARY OF THE INVENTION

It is an object of the invention to provide a composite aluminium panel comprising corrugated aluminium stiffener sheet that combines a 20% higher strength than standard AA3004 alloy with good roll formability at these higher strengths and with good weldability. It is another object of the invention to provide a composite  
25 aluminium panel having a good corrosion resistance. It is a further object of the invention the provide a composite aluminium panel which is easy and reliable to manufacture.

According to the invention in one aspect there is provided a composite aluminium panel comprising two parallel plates and/or sheets secured to the peaks and troughs of a  
30 corrugated aluminium stiffener sheet between the parallel plates and/or sheets, wherein the corrugated aluminium stiffener sheet is made from an aluminium alloy rolled sheet of composition (in weight percent):

	Mg	1.5 – 6.0	
	Mn	0.3 – 1.4	
	Zn	0.4 – 5.0	
	Fe	up to 0.5	
5	Si	up to 0.5	
	Zr	up to 0.30	
	optionally, one or more of		Cr 0.05 - 0.30
			Ti 0.01 – 0.20
			V 0.05 – 0.25
10			Ag 0.05 - 0.40
			Cu up to 0.40
	others up to 0.05 each, 0.15 total		
	Al	balance	

and having in an H-condition or in the O-condition a ratio of PS/UTS in the range of  
15 0.4 to 0.9 and having good roll formability.

PS and UTS stand for 0.2% proof strength and ultimate tensile strength respectively. The H-condition as indicated above is typically an H<sub>xy</sub>-condition or modifications thereof, where x is in the range of 1 to 3 and y is in the range of 1 to 6, or modifications thereof.

20 By the invention a surprisingly good combination is achieved of 20% or more higher strength levels than standard AA3004 in soft and strain hardened tempers, a good formability at these higher strength levels and a good weldability. This combination in the corrugated stiffener sheet is achieved due to the compositional window and a suitable grain structure. In combination, they provide good bendability, a  
25 work hardening index "n" is the range of 0.10 to 0.40 at higher strengths levels of 20% improvement or more than AA3004 in comparable tempers and gauges, and good roll formability having bendability of one times thickness in the H<sub>x</sub>6 tempers, with x in the range of 1 to 3, or in the soft temper. Using corrugated sheet with improved strength levels made out of the aluminium rolled sheet product set out above, allows for  
30 designing and constructing of composite panel structures which are lighter than the conventional structures, in particular those based on extruded aluminium alloys. Aluminium rolled sheet products of the defined composition have also been found with

good corrosion resistance. This allows the composite panels to be applied in corrosive environments such as a marine environment when applied in a ship or offshore construction.

Roll formability of AA5000 series alloy sheet products may be assessed by means of their bendability performance. Bendability of a material may be tested in accordance with ASTM E-290. During this test a sheet material will be bend for 180° over a mandrel having the same thickness at the sheet material itself; indicated above as bendability of one times thickness. The convex surface of the bend is visually examined for the presence of cracks. The presence of one or more cracks larger than 1 mm indicated a "fail" bendability performance resulting in the sheet material to be rejecting for roll forming. The bendability performance is indicated as "good" in case there are no cracks larger than 1 mm can be seen on the convex surface of the bend.

In a preferred embodiment the corrugated aluminium stiffener sheet has a ratio of PS/UTS in the range of 0.4 to 0.8, and more preferably in the range of 0.4 to 0.7, to enhance roll formability.

In an embodiment the gauge of the corrugated aluminium stiffener sheet is in the range of up to 3.0 mm, and more preferably in the range of 0.2 to 1.0 mm gauge sheets.

The corrugated aluminium sheet may additionally be provided as patterned or embossed sheet.

The reasons for the limitations of the alloying elements in the corrugated aluminium stiffener sheet for application in the composite aluminium panel according to the present invention are described below. All composition percentages are by weight.

Mg is the primary strengthening element in the alloy. Mg levels below 1.5% do not provide the required strength and when the addition exceeds 6.0% severe cracking occurs during the casting and hot rolling of the product. The preferred level of Mg is between 3.0 to 5.6% as a compromise between fabricability and strength.

Mn is an essential alloying element. In combination with Mg the Mn provides the strength to the alloy product in both welded and non-welded condition. Mn levels below do not provide sufficient strength to the welded joints of the alloy product. Above 1.4% the hot rolling becomes extremely difficult. The preferred maximum limit

for Mn is 0.9% which represents a compromise between strength and fabricability. More preferably the ratio Fe/Mn is in the range of 0.3 to 1.0.

Zn is an important alloying element since it improves corrosion resistance in the alloy product when it is present in a range of up to 1.2%, preferably up to 0.9%. Further zinc serves as a strengthening element by age hardening in combination with Mg when the Zn is present in a range of 3.0 to 5.0%. In the latter case it is preferred to maintain a Zn/Mg-ratio in the range of 1.1 to 5, and preferably in the range of 4 to 5. When the Zn level is above 5.0% casting and subsequent hot rolling becomes more difficult, in particular at an industrial scale. Below 0.4% the effect of Zn is less significant, so as a consequence a minimum of 0.4% is required, and more preferably a minimum of 0.5%.

The Fe in the alloy product may form primary compounds of the Al-Fe-Mn type during casting and thereby limiting the beneficial effects due to the Mn as alloying element. Fe levels above 0.5% causes coarse primary particles formation and which decrease the formability of the alloy product. The preferred range of Fe is 0.15 to 0.30%, more preferably 0.20 to 0.30%.

The Si also combines with Fe to form coarse AlFeSi phase type particles and which can affect the formability of the alloy product. Further Si limits the beneficial effects of Mg. To avoid any unacceptable loss in formability the Si level must be kept below 0.5%. The preferred range for Si is 0.07 to 0.20%, and more preferably 0.10 to 0.20%.

The Zr is an important alloying element for achieving strength improvements. Further the Zr is important to improve the resistance against cracking during welding of the alloy products in accordance with this invention. Zr at a level above 0.3% results in coarse needle shaped primary particles that decrease fabricability of the alloy product and further decrease bendability of the obtained product. As a compromise between strength and formability a preferred range of 0.05 to 0.25% is required.

Ti is important as a grain refiner during solidification of both ingots and welded joints produced using the alloy product in accordance with the invention. However, Ti in combination with Zr can form undesirable coarse primary phases. In order to avoid this the Ti level in the presence of Zr should be kept below 0.2%, and preferably below 0.10%, the most preferred range for Ti is 0.01 to 0.10%.

Cr is an optional alloying element for further improving the corrosion resistance of the alloy product. However, Cr limits the solubility of both Mn and Zr. Therefore, to avoid the formation of coarse primary phases, the Cr level must be kept below 0.3%. A preferred range for Cr is up to 0.15%.

5 V is an optional alloying element, and may be used to substitute or in addition to Cr. The preferred range is from 0.05 to 0.25%. A more preferred maximum range for V is up to 0.15%.

Cu levels above 0.4% give rise to unacceptable deterioration in the pitting corrosion resistance of the alloy product. The preferred maximum level for Cu is up to 10 0.25%, and more preferably up to 0.1%.

Silver is an optional alloying element that can improve further the stress corrosion resistance of the alloy product. If added the presence should be limited to 0.4% and the minimum level in the alloy product is preferably at least 0.05%.

The balance is Al and inevitable impurities. Typically each impurity element is 15 present at 0.05% maximum and the total of impurities is 0.15% maximum.

A very successful embodiment of the composite aluminium panel in accordance with the invention is where the corrugated aluminium stiffener sheet is further characterised by the following composition in weight percent:

	Mg	5.0 – 6.0, preferably 5.0 – 5.6
20	Mn	0.6 – 1.2
	Zn	0.4 – 1.5, preferably 0.4 – 0.9, more preferably 0.5 – 0.9
	Zr	0.05 – 0.25
	Cr	up to 0.3
	Ti	up to 0.2
25	Fe	up to 0.5, preferably 0.2 – 0.3
	Si	up to 0.5, preferably 0.1 – 0.2
	Cu	up to 0.4, preferably up to 0.1
	Ag	up to 0.4

balance Al and inevitable impurities.

30 With this embodiment it is achieved that a composite aluminium panel is provided of which the stiffener sheet combines a 20% or more higher strength than the standard AA3004 alloy in a comparable gauge and temper, with a good formability at

these higher strength levels when assessed by means of bendability in accordance with ASTM E-290, with good weldability, and with a good corrosion resistance. The aluminium alloy product has very good formability in particular at gauges in the range up to 3.0 mm, and more preferably at gauges in the range of 0.2 to 1.0 mm. Further it  
5 has been found that this corrugated sheet material retains its shape after roll forming much better, viz. less springback, than conventional AA5xxx-series aluminium alloys, such as AA5083 and AA5456. Further this successful embodiment allows for high speed laser welding, typically in the range of 3 to 10 m/min and preferably in the range of 4 to 6 m/min, for the production of composite panels comprising at least one  
10 corrugated sheet made out of the aluminium sheet product as set out above. The good weldability, and in particular the good laser weldability, of the corrugated stiffener sheet as set out above, was unexpected over previous experience in the art with conventional high magnesium AlMg-alloys, such as AA5083 and AA5456.

In a more preferred embodiment the corrugated aluminium sheet in the O-temper  
15 has a minimum 0.2% proof strength (PS) of 110 MPa or more for gauges of up to 3 mm, and more preferably of 115 MPa or more, and most preferably of 120 MPa or more. For gauges of up to 3 mm the aluminium alloy product in the O-temper has a minimum ultimate tensile strength (UTS) of 270 MPa or more, preferably of 280 MPa or more, more preferably of 300 MPa or more, and most preferably of 310 MPa or  
20 more.

In a further embodiment of the composite aluminium panel in accordance with this invention the corrugated aluminium sheet may be provided with a cladding on at least one side of the surface of the rolled sheet of the following:

- (i) it is of a higher purity aluminium alloy than said rolled sheet;
- 25 (ii) the cladding is of the Aluminium Association AA1000 series;
- (iii) the cladding is of the Aluminium Association AA6000 series;
- (iv) the cladding is of the Aluminium Association AA7000 series.

In this embodiment the cladding is brought onto the corrugated sheet prior to roll forming the sheet product into a corrugated profile. The corrugated aluminium sheet in  
30 accordance with the invention has a very good corrosion resistance. However, in certain extreme corrosive environments it may be useful to provide a cladding which further enhances to the corrosion resistance of the alloy product. Such clad products utilise a



core of the aluminium alloy composition set out above and a cladding of higher purity which in particular corrosion protects the core. The cladding includes essentially unalloyed aluminium or aluminium alloys containing not more than 0.1 or 1% of all other elements. Aluminium alloys herein designated 1xxx-type series include all  
5 Aluminium Association (AA) alloys, including the sub-classes of the 1000-type, 1100-type, 1200-type and 1300-type. In addition it has been found that aluminium alloys of the AA6000-series, including the sub-classes, and which contain typically more than 1% of alloying additions, can serve as cladding. And in addition it has been found that  
10 aluminium alloys of the AA7000-series, including the sub-classes, and which contain typically more than 0.8% of zinc as alloying element, can serve as cladding, such as AA7072. Other aluminium alloys could also be useful as cladding as long as they provide in particular sufficient overall corrosion protection to the core alloy product.

In a very advantageous embodiment of the composite aluminium panel of the invention, the corrugated aluminium stiffener sheet may be provided with a clad layer  
15 of an AA4000-series alloy, such as for example AA4047. In this embodiment the clad layer or layers are not primarily present to provide an improved corrosion resistance, although it may give a contribution, but it allows the corrugated aluminium sheet to be welded or brazed to another sheet, plate or extrusion product into prefabricated products. In the case of corrugated aluminium sheet clad with AA4000-series alloys,  
20 there is no need to provide filler wire during welding in cases where it is otherwise required. Further the structural integrity of the aluminium sheet is maintained, as a consequence higher Zn-levels can be present in the alloy product without affected the corrosion resistance of the heat-affected zone. The thickness of the clad layer should be sufficient to prevent loss of adhesion from the corrugated aluminium sheet and to  
25 protect the corrugated aluminium sheet from the heat affected zone. In case of brazing, it is possible to braze such clad corrugated sheet with another sheet or plate or extrusion into one piece at a temperature in the range where AA4000-series alloys can be melted. The brazing can be carried out with or without controlled atmosphere.

The clad layer or layers are usually much thinner than the core, each constitute 1  
30 to 15 or 20 or possibly 25% of the total composite thickness. A cladding layer more typically constitutes around 5 to 12% of the total composite thickness.

The corrugated aluminium stiffener may be secured to a parallel plate or sheet by means of mechanical fastening elements or adhesion. In a preferred embodiment the corrugated aluminium stiffener is being secured to a parallel plate or sheet by weld lines extending along the peaks or troughs. This allows for a fast and economic and reliable production of composite panels. The weld lines can be obtained by using any one or combinations of the standard welding techniques, e.g. MIG, TIG, stir welding, friction stir welding, etc. In a further preferred embodiment the weld lines are obtained by laser welding techniques. Further at least one of the plates or sheets has on the other surface no visible weld lines, but a internal weld line structure where each line of which passes through a trough or peak and into the material of the plate or sheet without however totally penetrating that material. This gives a composite aluminium panel with weld lines on one face and smooth surface on the other face.

In an alternative embodiment the corrugated aluminium stiffener is being secured to a parallel plate or sheet by means of brazing. In this embodiment the corrugated aluminium stiffener is being made from the aluminium alloy product of the invention with a cladding from the AA4000-series alloys, as set out above.

In a preferred embodiment the corrugated aluminium stiffener between the panels has flat peaks and troughs.

Most typically, but not by way of limitation the composite aluminium panel is of a thickness such that the spacing between the external plates and/or sheets lies between 10 and 300 mm, more preferably between 10 and 200 mm. The surface plate/or sheet in such an instance is up to 25 mm thick in typical embodiment, and the corrugated aluminium stiffener is within the range of up to 6 mm thick, preferably up to 3 mm thick, and most preferably in the range of 0.2 to 1.0 mm thickness. By using the aluminium alloy product of the invention at these relatively thin gauges and applied in a composite aluminium panel as set out above, it is achieved that significant weight reduction can be obtained in constructions while maintaining at least the same strength and/or stiffness levels as previously known in the art.

It will be found usually preferable to have the two parallel plates and/or sheets portions each equal to or thicker than the metal thickness of the corrugated aluminium stiffener.

The parallel plates or sheets are preferably made out of aluminium alloy, and in case the corrugated aluminium stiffener is welded to a plate or sheet, the plate or sheet is preferably made of a weldable aluminium alloy. In a more preferred embodiment the plates and/or sheets are within the same compositional window as the corrugated aluminium stiffener obtained from an aluminium rolled product set out above.

In a further aspect of the invention there is provided in a welded panel construction comprising the composite aluminium panel of the invention and/or a corrugated sheet product of the invention. Such a welded panel construction further comprises of two aluminium profiles, typically U-, H- or T-shaped, made via extrusion or bending an plate or sheet product, where the composite aluminium panel is aligned between said two profiles. The panels are very simple and reliable to manufacture, and can be aligned in a practical manner in a workshop or a yard. Due to the closed structure of the panel, they are easy to transport and during transportation damage of the internal structure comprising the corrugated sheet or sheets is prevented.

The type of composite aluminium panel defined above can be used alone, for example for bulkheads, or like sub-divisions. However, two or more composite panels can themselves be linked together and form a parallel composite to define for example a hull compartment including sub-divisions or other large-scale metal constructions, such as truck or rail car floors, bridges and especially ships.

According to the invention in another aspect there is provided in the application of the composite aluminium panel as set out above in a welded structure, such as but not limited to the application in marine shipbuilding and marine offshore constructions. Further the composite aluminium panel may be applied in civil and railroad fields and the like, where lighter constructions are desired preferably having a good corrosion resistance.

Further the invention relates to the use of aluminium rolled material having a chemical composition as set out above and in the claims, as corrugated stiffener sheet and/or as parallel sheet or plate in the composite aluminium panel in accordance with the invention.

## EXAMPLES

The invention will now be illustrated by several non-limitative embodiments and examples, with reference to the accompanying drawings, in which:

Fig. 1A to 1C show cross-sections of several embodiments of corrugated sheet;

5 Fig. 2A to 2C show cross-sections of several embodiments of composite aluminium panels;

Fig. 3A and 3B show in cross-sections a composite aluminium panel in connection with I-shaped beams;

10 Fig. 4 shows a perspective view of a composite aluminium panel in connection with an I-shaped beam;

Fig. 5 shows schematically the steps of assembling a panel of the invention;

Fig. 6 shows cross-sections of the panels of the invention in connection to each other or to the wall or hull of a vessel.

Fig. 1 shows schematically typical shapes of roll formed corrugated aluminium sheet, as seen in cross-section perpendicular to its direction of elongation. The corrugated aluminium sheet can be applied as a stiffener sheet in a composite aluminium panel in accordance with this invention. Fig. 1A and 1B show flat peaks and troughs, and where Fig. 1B has a dovetail shape. An alternative embodiment is shown in Fig. 1C where the corrugated aluminium sheet has curved peaks and troughs. The indicated dimensions a, b, c, and d are typically in the range of 10 to 300 mm.

25 Fig. 2A and 2B show schematically, as seen in cross-section perpendicular to its direction of elongation, composite aluminium panels of the invention where a corrugated aluminium stiffener is arranged between two parallel sheets and/or plates. The embodiment of Fig. 2C shows schematically, as seen in cross-section perpendicular to its direction of elongation, a composite aluminium panel where the corrugated aluminium stiffener comprises two corrugated sheets each with flat peaks and troughs and whereby the peak of one sheet is joined to the trough of the other corrugated sheet. The arrows in Figs. 2A to 2C show the location of weld lines for securing the various sections to each other.

30 Fig. 3A and 3B show schematically, as seen in cross-section perpendicular to its direction of elongation, a composite aluminium panel of the invention being secured to

I-shaped beams or profiles by means of securing at least one of the parallel plates or sheet of the composite aluminium panel to the I-shaped beam.

Fig. 4 show schematically a perspective view of composite aluminium panels are connected to each other in their direction of elongation. For this the following procedure can be used: firstly produce a section which fits with the contours of the corrugated shape, secondly open the top plating to expose the corrugated shape, thirdly place a "connecting corrugated section" on to the panels to be joined such that the "connecting corrugated section" is equally partitioned between the two sandwich panels, then join at those points marked as "xxxx" in the figure. The above procedure then securely fastens any two sandwich panels of current invention along the width direction. Alternatively sandwich panels can be produced in such away that one of the two top plates can be shorter than the other to allow ease of joining along the width direction.

Fig. 5 shows schematically how a panel in accordance of the invention can be assembled. A panel comprises of two aluminium U-, H- or T-shaped profiles, which profiles can either be made by extrusion or bending of a sheet or plate, said profiles being connected, preferably by means of welding at selected locations, by a first sheet of the aluminium product of the invention to one of the legs of each profile forming a bottom of the panel, see step 1 in Fig. 5. Subsequently, a pre-formed corrugated sheet or sheets are connected to said bottom of the panel, see step 2 in Fig.5. And in a third step a top plate or sheet is connected, preferably by means of welding, to both the corrugated sheet and the other leg of each profile. The profiles have a typical thickness of 3 mm. In this way a very simple and effective way of manufacturing panels is being provide. The panels of the invention are simple to align in for example a workshop or a yard, and can be connected to form a transverse frame or can be connected via welding to the side walls of for example the hull of a ship in a very practical manner, as shown in Fig. 6. Further the panels are closed, are easy the handle and prevent damage of the enclosed corrugated sheets during transportation.

#### Example 1

An alloy within the compositional range of the invention, having the following chemical composition (in weight percent): 5.20% Mg, 0.84% Mn, 0.50% Zn, 0.13% Zr, 0.013% Cu, 0.049% Cr, 0.19% Fe, 0.11% Si, 0.015% Ti, balance aluminium and

inevitable impurities, has been DC-cast on an industrial scale to an ingot having dimensions of 440x1480x4800 mm. The ingot has been preheated for 15 hours at 510 °C, then hot rolled at about 500 °C to produce 4mm gauge products. Prior to subsequent cold reduction, an intermediate anneal at 350 °C for a period of 2 hours has been applied. The annealed and hot rolled product was subsequently cold rolled to 2 mm gauge sheet. A second interanneal has been applied at 350 °C for a period of 2 hours. Followed by cold rolling to a final gauge of 1.0 mm and then final annealed with similar conditions as the interannealing in order to produce a soft temper product.

The material has been assessed in accordance with EURO-norm 10,002 for its tensile properties in the LT-direction. Further the material has been assessed for its formability by testing the bendability in accordance with ASTM E-290. During this bendability test 1.0 mm gauge sheet material of 120x45 mm has been bent for 180° over a mandrel with the same thickness as the sheet material, viz. 1.0 mm. The bent specimens have been visually examined for the appearance of cracks on the convex surface of the bend. The outcome of this test is indicated by specifying good or fail. By the term "fail" it is indicated that there was at least one crack of 1mm or more on the convex surface of the bend.

The results are listed in Table 1 where a comparison has been made with samples of standard AA3004 material in the O-temper. From these results it can be seen that the aluminium alloy product applied in accordance with this invention has a more than 20% higher strength level than AA3004 material in the same temper and with the same gauge, in this particular case an improvement of more than 45% has been achieved, while the bendability is at least equivalent to standard AA3004.

Table 1

Material	Temper	Gauge [mm]	0.2% PS [MPa]	UTS [MPa]	Elong. [%]	Bendability
Invention	0	1.0	132	315	20.1	good
			135	316	20.3	good
			129	314	19.9	good
			131	316	20.7	good
AA3004	0	1.0	65	157	14.0	good
			67	158	14.5	good
			69	155	14.3	good
			66	159	14.2	good

Example 2

Sheet material with dimensions of 1200x250 mm and of 1.0 mm thickness of standard AA3004 and material identical to the material of Example 1 and being within the preferred ranges set out in the claims, both materials were in the O-temper, were subjected a welding testing. Two identical sheets were welded together using a 12 kW CO<sub>2</sub> laser equipment, operating at 6 kW and with a line speed of 5 m/min. Tensile samples with weld beads were produced from such "through welded" sheets and tested for tensile properties.

The results are listed in Table 2. From these results it can be seen that after welding the aluminium product in accordance with the invention has at least 20% higher tensile properties than standard AA3004 material at similar gauges and temper. Further this example shows that the product of this invention may be welded at very thin gauges using laser techniques at relatively high welding line speeds. Further it has been found that when the base material is in the O-temper, the properties of the base material are essentially responsible for the mechanical properties after welding and not the welding technique applied. This can also be found from the results as listed in Table 1 and 2 where the material in accordance with the invention have mechanical properties in the same range. Further it has been found that the corrugated aluminium sheet applied in accordance with the invention is easy to laser weld, and in particular CO<sub>2</sub> laser welding, contrary to most conventional high Mg 5000-series alloys having a much lower zinc content. These conventional high AlMg alloy have more scatter of the laser beam by the welding-melt-pool. It allows the present corrugated aluminium sheet to be applied with wider ranges in laser welding as compared to standard high AlMg-alloys alloys such as AA5456.

Table 2

Material	0.2% PS [MPa]	UTS [MPa]	Elongation [%]
invention	132	315	20.1
	136	316	20.3
	131	314	19.9
AA3004	66	155	13.1
	69	152	14.2
	66	158	14.5

Example 3

Using the same processing route as with Example 1 sheet material which can be applied as corrugated aluminium sheet in accordance with the invention and having the same chemical composition has been produced with a final gauge of 1.3 mm. The two different final annealing treatment have been applied, after which the tensile properties have been determined in accordance with EURO-norm 10,002 in both the L- and LT-direction. The two final anneals applied were: (1) soak time of 1 hour at 250 °C; and (2) soak time of 1 hour at 350 °C. In both cases the heating up rate was 25 °C/hour and the cooling rate to below 100 °C after final annealing was 10 °C/hour. Annealing of type (1) results in an H-temper and of type (2) results in an O-temper. The results are listed in Table 3. From these results it can be seen that the aluminium sheet applied in the composite aluminium panel in accordance with the invention can be provided in the O-temper and in an H-temper, in both cases having strength levels of at least 20% improvement over standard AA3004 material.

Table 3

Annealing type	Gauge [mm]	L-direction			LT-direction		
		PS [MPa]	UTS [MPa]	Elong. [%]	PS [MPa]	UTS [MPa]	Elong. [%]
(1)	1.3	252	370	9.6	254	370	12.3
		254	372	11.0	255	371	12.5
(2)	1.3	128	317	14.7	126	311	20.2
		128	318	15.9	127	314	19.9



**CLAIMS**

1. A composite aluminium panel comprising two parallel plates and/or sheets secured to the peaks and troughs of a corrugated aluminium stiffener sheet between the parallel plates and/or sheets, wherein the corrugated aluminium stiffener sheet is made from an aluminium alloy rolled sheet of composition (in weight percent):

Mg 1.5 – 6.0

Mn 0.3 – 1.4

Zn 0.4 – 5.0

Fe up to 0.5

Si up to 0.5

Zr up to 0.30

optionally, one or more of Cr 0.05 - 0.30

Ti 0.01 – 0.20

V 0.05 – 0.25

Ag 0.05 - 0.40

Cu up to 0.40

others up to 0.05 each, 0.15 total

Al balance

and having in an H-condition or in the O-condition a ratio of PS/UTS in the range of 0.4 to 0.9 and having good roll formability.

2. A composite aluminium panel according to claim 1, wherein the corrugated aluminium stiffener sheet has a thickness in the range of up to 3.0 mm, and preferably in the range of 0.2 to 1.0 mm.

3. A composite aluminium panel according to claim 1 or 2, wherein the Zn content of the corrugated aluminium stiffener sheet is in the range of 0.4 to 1.2%.

4. A composite aluminium panel according to claim 1 or 2, wherein the Zn content of the corrugated aluminium stiffener sheet is in the range of 3.0 to 4.5%.

5. A composite aluminium panel according to any one of claims 1 to 3, wherein the corrugated aluminium stiffener sheet is made from an aluminium alloy rolled sheet of composition (in weight percent):

5	Mg	5.0 - 6.0
	Mn	0.6 - 1.2
	Zn	0.4 - 1.5, and preferably 0.4 - 0.9
	Zr	0.05 - 0.25
	Cr	up to 0.3
10	Ti	up to 0.2
	Fe	up to 0.5
	Si	up to 0.5
	Cu	up to 0.4
	Ag	up to 0.4
15	balance Aluminium and inevitable impurities.	

6. A composite aluminium panel in accordance with any one of claims 1 to 5, wherein a cladding is present on at least one side of the surface of the corrugated sheet of the following:

- 20 (i) it is of a higher purity aluminium alloy than said rolled sheet;  
(ii) the cladding is of the Aluminium Association AA1000 series;  
(iii) the cladding is of the Aluminium Association AA6000 series;  
(iv) the cladding is of the Aluminium Association AA4000 series;  
(v) the cladding is of the Aluminium Association AA7000 series.

25

7. A composite aluminium panel in accordance with any one of claims 1 to 6, wherein the two parallel plates and/or sheets have been secured to the corrugated aluminium stiffener sheet by means of welding, and preferably by means of laser welding.

30

8. A composite aluminium panel in accordance with any one of claims 1 to 7, wherein at least one of the two parallel plates and/or sheets are within the same compositional window as the corrugated aluminium stiffener.
- 5 9. A composite aluminium panel in accordance with claim 6 or 8, wherein a cladding of the AA4000-series aluminium alloy is present on at least one side of the surface of the corrugated aluminium stiffener sheet, and wherein at least one of the two parallel plates and/or sheets has been secured to the corrugated aluminium stiffener sheet by means of brazing.
- 10 10. Use of an aluminium rolled product of composition (in weight percent):
- |                            |                                    |
|----------------------------|------------------------------------|
| Mg                         | 1.5 – 6.0                          |
| Mn                         | 0.3 – 1.4                          |
| Zn                         | 0.4 – 5.0                          |
| 15 Fe                      | up to 0.5                          |
| Si                         | up to 0.5                          |
| Zr                         | up to 0.30                         |
| optionally, one or more of | Cr 0.05 - 0.30                     |
|                            | Ti 0.01 – 0.20                     |
| 20 V                       | 0.05 – 0.25                        |
|                            | Ag 0.05 - 0.40                     |
|                            | Cu up to 0.40                      |
|                            | others up to 0.05 each, 0.15 total |
|                            | Al balance                         |
- 25 as corrugated aluminium stiffener sheet and/or as parallel sheet or plate in a composite aluminium panel in accordance with any one of claims 1 to 9.
11. Use of an aluminium rolled product of composition (in weight percent):
- |       |                                     |
|-------|-------------------------------------|
| 30 Mg | 5.0 - 6.0                           |
| Mn    | 0.6 - 1.2                           |
| Zn    | 0.4 - 1.5, and preferably 0.4 - 0.9 |

	Zr	0.05 - 0.25
	Cr	up to 0.3
	Ti	up to 0.2
	Fe	up to 0.5
5	Si	up to 0.5
	Cu	up to 0.4
	Ag	up to 0.4

balance Aluminium and inevitable impurities.

10 as corrugated aluminium stiffener sheet and/or as parallel sheet or plate in a composite aluminium panel in accordance with any one of claims 1 to 9.

12. A welded structure comprising at least one composite aluminium panel according to any one of claims 1 to 9.
- 15 13. A composite aluminium panel according to any one of claims 1 to 9 for ship building.
14. A composite aluminium panel according to any one of claims 1 to 9 for marine offshore construction.




Fig. 1A




Fig. 1B




Fig. 1C




Fig. 2A




Fig. 2B




Fig. 2C




Fig. 3A




Fig. 3B






Fig. 4

**Step 1:** Connect bendet plate or profile  
to bottom plate



**Step 2:** Connect corrugated sheet  
to bottom plate



**Step 3:** Connect top plate to bendet plate  
or profile and to corrugated sheet





Fig. 5

Connection panel to panel



Connection panel to hull




Fig. 6